



CLEAR LLDPE / EVOH DIGITAL SEALANT WEB DWS002

PRODUCT DESCRIPTION:

Clear LLDPE-EVOH coex film with excellent sealability, and low O₂TR, that meets diverse end use requirements

APPLICATIONS AND FEATURES:

- Applications requiring excellent sealability, hot tack, and low oxygen transmission

PROPERTIES	TEST METHOD	UNIT		NOMINAL RESULTS			
Thickness	ASTM D6988	mil		2.0	3.0	3.5	4.0
Yield	ASTM D4321	in ² /lb		14,871	9,914	8,498	7,435
Ultimate Tensile Strength	ASTM D882	psi	MD	4,500	4,500	4,500	4,500
			TD	4,000	4,000	4,000	4,000
1% Secant Modulus	ASTM D882	psi	MD	50,000	50,000	50,000	50,000
			TD	54,000	54,000	54,000	54,000
Elongation	ASTM D882	%	MD	600	600	600	600
			TD	700	700	700	700
COF	ASTM D-1894			0.20-0.40	0.20-0.40	0.20-0.40	0.20-0.40
Elmendorf Tear	ASTM D1922	gf	MD	500	650	700	800
			TD	1000	1400	1600	1600
Seal Initiation	F88	°F		200	200	200	200
O ₂ TR, (cc/100in ² /day at 23°C/0%RH)	ASTM D1434			0.12	0.11	0.09	0.07

*MD = Machine Direction *TD = Transverse Direction

Storage & Handling: Needs to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing.

Food Contact: Complies with EC (EU 202/2014 & EU 10/2011) and FDA (21 CFR § 175.105 & 21 CFR § 175.300) regulations on packaging for direct contact with foodstuffs. Specific document and MSDS are available on request.

Disclaimer: The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. StockPKG makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract.