

## High Barrier Easy Peel Thermoforming Film THF003

## 6 Mil

High Barrier Easy Peel Thermoforming Film is a co-extruded PA // EVOH // PE film. Industry leading clarity and great forming draw characteristics.

PROPERTIES	TEST METHOD	UNIT		TARGET	MINIMUM	MAXIMUM
Thickness	Internal	Mil		6	5.7	6.3
		Micron		150	142.5	157.5
Yield	ASTM D 4321	m²/kg		6.47	6.15	6.80
		in²/lb		4,551	4,324	4,779
Tensile Strength @ break	ASTM D 882	N/mm²	MD	> 24.52		
			TD	> 22.56		
Elongation @ break	ASTM D 882	%	MD	> 300		
			MD	> 300		
Coefficient of Friction	ASTM D 1894		Kinetic	0.2	0.1	0.3
Dart Impact Strength (@ 1.52 Meter Height)	ASTM D 1709	gf		≥ 280		
Seal Strength (125°C, 1.8 second dwell time)	ASTM F 88	N/inch		≥ 7.85		
W.V.T.R (38°C 90%RH)	ASTM F 1249	gm/100in²/24hrs		< 0.34		
O.T.R. (23°C, 0% RH)	ASTM D 3985	cc/100in²/24hrs		< 0.10		

<sup>\*</sup> MD = Machine Direction, \* TD = Transverse Direction

**Storage & Handling:** Needs to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing.

Food Contact: Complies with EC (EU 202/2014 & EU 10/2011) and FDA (21 CFR § 175.105 & 21 CFR § 175.300) regulations on packaging for direct contact with foodstuffs. Specific document and MSDS are available on request.

**Disclaimer:** The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. StockPKG makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract.