

HIGH DENSITY BOPE FILM (BOPE01)

HIGH DENSITY BOPE FILM

A proprietary film, only offered by StockPKG Films. With high stiffness and enhanced visual clarity, this film boasts excellent machinability and incredible printability. A TRUE ready-recyclable product, when used with eco-friendly inks.

BOPE offers a significant leap in performance for the sustainable films market. Compared to other Machine Direction Oriented PE films, StockPKG BOPE has the best clarity and machinability available in today's market.

FFATURES:

- Printing available on both face (rotogravure and flexography) or adhesive/varnish application
- · Excellent dimentional stability

APPLICATION:

• Suitable for use as secondary packaging and lamination, among other uses.

PROPERTIES	TEST METHOD	UNIT		TOLERANCE	THICKNESS (µm)		
				10%	20	25	40
Weight	Internal Method	g/m²		10%	19.10	24.5	38.0
Theoretical Density	Internal Method	kg/m³		-	950		
COF	ISO 8295	-		-	≤ 0.35		
Yield		in²/lb		-	36,812	28,700	18,500
Tensile Strength at Break	ISO 527	MPa	MD		≥ 90		
			TD	1 -	≥ 160		
Elongation at Break	ISO 527	%	MD	_	≤ 240		
			TD	<u>-</u>		≤ 100	
Thermal Shrinkage	Internal Method	%	MD			≤ 2.5	
			TD	<u>-</u>		≤ 1	
	Internal Method	%	MD			≤ 6	
			TD	-		≤ 3.5	
Young Modulus	ISO 527-1	MPa	MD			≥ 1200	
			TD		≥ 1750		
Haze	ASTM D 1003	%	Т	-	≤ 13 ≤		≤ 20
Clarity	ASTM D 1003	%	Т	-	≥ 70		
Gross 45°	ASTM D 2475	GU	Т		≥ 50 ≥ 45		45
Treatment	ASTM D 2578	Dyne/ cm	Outside		≥ 40		
			Inside	-	≥ 38		

*MD = Machine Direction *TD = Transverse Direction, *T = Treated Face, *NT = Untreated Face

Storage & Handling: Needs to be stocked in a closed warehouse & should not be exposed to direct sun light or light sources. Avoid extreme of humidity and heat. It is recommended to store below 40°C in dry places in original packing.

Food Contact: Complies with EC (EU 202/2014 & EU 10/2011) and FDA (21 CFR § 175.105 & 21 CFR § 175.300) regulations on packaging for direct contact with foodstuffs. Specific document and MSDS are available on request.

Disclaimer: The information given above is to the best of our knowledge and experience. Some of the properties can be changed as a result of suppliers' efforts to improve upon the quality or production efficiency of the subject. The information is believed to be true and accurate and is not intended to violate any statutory condition or right of a third party. StockPKG makes no warranty, express or implied, as to the fitness of the product for any specific use or purpose. The above data is purely for readers' consideration, investigation and verification and should be read in conjunction with the conditions for sale or contract.